



ZeraBrite™ CL-121

Advanced UV-resistant polyaspartic Coating

DESCRIPTION

ZeraBrite™ CL-121 is a high solids, low viscosity two-component, polyaspartic ester coating. It is available in crystal clear and a number of standard colours. It provides outstanding UV resistance, gloss retention, and color fastness.

ZeraBrite™ CL-121 is a highly attractive glossy finish, durable with exceptional toughness, mechanical strength, abrasion, and scratch resistance

ZeraBrite™ CL-121 is an all-weather, all-season, fast-curing coating. It cures at low temperatures down to 2°C (35°F). It is also ideal for fast turn-around projects, particularly during shut-down maintenance. It has 4 hours for foot traffic exposure, and it can sustain vehicular traffic in 24 hours.

WHERE TO USE

ZeraBrite™ CL-121 is recommended as a clear topcoat for aesthetics and protection of decorative epoxy flooring systems such as metallic, multi-colored quartz, textured flake-embedded flooring as well as pure white floors.

It is also suitable for residential garage floors, as well as exterior coating for commercial parking garage decks, porches, balcony decks, and swimming pool paint.

BENEFITS

- Attractive high gloss coating with exceptional clarity
- Convenient one-to-one mixing ratio
- Rapid cure and hardness development
- Extended working time
- High solids, zero VOCs
- Cures down to 2°C (36°F)
- Superior abrasion, scratch, and mar resistance
- Highly resistant to staining and yellowing
- Resistant to water immersion, petroleum, and common chemicals
- Easy to clean and maintain

HANDLING PROPERTIES @ 25°C (77°F)

Mixing Ratio, by volume	1 part A: 1 part B
Viscosity (Mixed)	500 cps
Solids (by volume)	81 %
Pot Life (working time).....	20 minutes
Foot Traffic (re-coat time)	4 hours
Vehicular Traffic.....	16 hours
Full Cure and Maximum Resistance	7 days

SURFACE PREPARATION

New concrete must be cured for a minimum of 28 days before applying ZeraBrite™ CL-121. The substrate must be dry and free of all dirt, waxes, previously applied coatings, oil, grease, laitance, and any foreign matter that may interfere with the bonding of the coating to the prepared substrate. Cracks and surface defects should be repaired prior to the application of the coating. Concrete surfaces that are to be coated should be mechanically abraded or shotblasted to provide a clean tooth for the coating application. If acid etching is the method of choice for the preparation of the concrete surface, the etched surface must be thoroughly flushed, neutralized, and dried (for at least 2 days) prior to the application of the coating.

Note: Although ZeraBrite™ CL-121 has outstanding UV resistance and color stability, being a clear coating, it will not stop the UV rays from going through it and can discolor the epoxy flooring beneath it. However, it will reduce the damage to a great extent.

MIXING

USE A VERY SLOW-SPEED MIXER. AVOID ENTRAPPING AIR INTO THE COATING. Mix Part A separately to obtain uniformity. Always use a stir stick to scrape the sides and the bottom of the mixing bucket. Pour the entire content of the liquid from the Part B container into the Part A container and mix thoroughly for 1-2 minutes until it is completely uniform.

APPLICATION

Pour a workable amount of the mixed coating onto the prepared substrate (or use a paint tray) and spread the material evenly with a short nap 6 mm lint-free roller. Always apply the coating once in a multi-directional manner (north-south, east-west) to provide an even coat at the proper thickness (8 mils wet). Care should be taken not to over roll the material as air may become entrapped in the coating. After 2 hours @ 23°C, apply the second coat in the same manner as the first if needed. Allow the coating to cure thoroughly for 2 hours for foot traffic exposure and 16-24 hours for vehicular traffic.

LIMITATIONS

- It is not recommended to use if the temperature is near the dew point or the relative humidity exceeds 85%.
- When using over an epoxy-based coating or primer, apply within the re-coat window or roughen the coating with sandpaper.
- Ensure that the surface is clean and dry.
- Apply in a thin coat (6 mils dry film thickness per coat) otherwise the solvent may become entrapped in the dry film.
- Not breathable; do not apply over an exterior slab-on-grade unless a vapor barrier is used.
- Do not leave the container opened; seal the container immediately. Part B in particular is very sensitive to moisture.

COVERAGE

Based on a 8 mils dry film thickness per coat over a smooth surface:

400-450 ft²/2 U.S. gallon/coat per 7.58L (2 U.S. gallon) unit

PACKAGING

7.58 litre (2 U.S. gal.) units

37.8 litre (10 U.S. gal.) units

CLEAN UP

Clean all equipment and installation tools immediately with xylene or acetone.

SAFETY PRECAUTIONS

Consult the Material Safety Data Sheet (MSDS) for specific instructions.

STORAGE

Store in a heated warehouse. Do not freeze.

SHELF LIFE

One year from the date of manufacture if kept in the original unopened containers under normal heated warehouse conditions.

WARRANTY

“The recommendations made and the information herein is the result of accurate laboratory and field tests under controlled conditions. We guarantee that the quality and properties of the materials supplied conform to our standards. Zeraus Products Inc. makes no warranties, expressed or implied, as uses and applications are beyond our control. Zeraus Products Inc. shall not be liable for any injury, loss, or damage (direct or consequential) arising from use or inability to use the products. Before using, the user is urged to pre-test the products in his/her own environment to determine the suitability of the products for their intended use, and the user assumes all risk and liability whatsoever in connection therewith.

Zeraus Products Inc.’s liability, if any, is limited to a refund of the purchased price or replacement of that portion of the merchandise proven to be defective. Zeraus Products Inc. shall have no other liability, including liability for incidental, consequential, or resultant damages, however, caused, whether due to breach of warranty, negligence, or strict liability.

This warranty may not be modified or extended by representatives of Zeraus Products Inc., its distributors or dealers.”