



ZeraDite™ W

Universal Waterborne Epoxy Primer & Sealer

DESCRIPTION

ZeraDite™ W is a versatile, fast-setting, two-component waterborne epoxy concrete primer. It is recommended for both floors and walls (concrete and drywall).

WHERE TO USE

ZeraDite™ W can be used as a damp surface concrete primer for interior or exterior applications. It is ideal as a primer in conjunction with ZeraDur (100% solids epoxy floor coating). It promotes adhesion to concrete surfaces and allows the concrete to be sealed from outgassing. It can be used on garage floors, slab-on-grade, porches, balcony decks, etc.

It is also suitable as a wall coating over primed drywall as well as concrete blocks (primed with block filler to fill surface irregularities). It is highly recommended for surfaces exposed to high humidity or surfaces subjected to moisture condensation areas such as shower rooms, food, and beverage processing plants, and wash bays.

BENEFITS

Safe & Easy to Use:

ZeraDite™ W is safe, clean, and easy to use. It has no odor and contains no volatile solvents or corrosive or hazardous materials.

Excellent Adhesion to Green Concrete:

ZeraDite™ W exhibits excellent adhesion to dry, damp, or green concrete surfaces (7 days cure). It can save time and money by reducing the waiting time for freshly applied concrete from the standard 28 days to 7 days.

Hot-Tire Pick-Up Resistance:

Due to its ability to resist hot-tire pickup, ZeraDite™ W is suitable as a damp surface concrete primer under

Epoxy residential garage floors. It is a perfect choice for do-it-yourself application.

Fast Setting:

ZeraDite™ W sets in 6 hours @ 23°C (74°F) which allows the topcoat to be applied on the same day. It is ideal for quick turn-around projects.

Breathable:

ZeraDite™ W prevents liquid from passing through into the concrete but remains breathable to allow moisture vapor, due to hydrostatic pressure from beneath the floor, to exit.

HANDLING PROPERTIES @ 23°C (74°F)

Mix Ratio (by volume)	4 Part A: 1 Part B
Solids (by volume)	65%
Mixed Weight (Density)	1.2 kg/litre (10 lb./US gal)
VOC Material (ASTM D 6886)	30 g/L
Pot Life.....	40 minutes
Re-coat Time.....	6 hours
Full Cure and Maximum Resistance	7 days
Colour.....	Light Grey

SURFACE PREPARATION

Although new concrete must be cured for a minimum of 28 days before applying any epoxy coating or primer, ZeraDite™ W can be applied as early as 7 days. The substrate must be above 120°C (54°F) and must be free of all dirt, waxes, previously applied coatings, oil, grease, laitance, and any foreign matter that may interfere with the bond of the primer to the prepared substrate. Cracks and surface defects should be repaired prior to the application of the primer. Concrete surfaces to be coated should be mechanically cleaned using planetary grinding machines or something similar in order to provide a clean tooth for the primer application.

MIXING

The mixing equipment used to mix the **ZeraDite™ W** must be a mud mixer or a ‘Jiffy Mixer’ on a slow-speed drill. The mixing equipment must be clean and free of any contaminants that may be present from previously used products. Mix component A first to eliminate the possibility of settlement.

APPLICATION

Pour a workable amount of the mixed coating into a paint tray and spread the material evenly with a roller. Using a lint-free 9 mm nap roller, apply the material to an even coat.

NOTE: YOU MUST HAVE GOOD AIR CIRCULATION TO ENSURE PROPER WATER RELEASE AND DRYING.

LIMITATIONS

- Waterborne epoxies should be applied at or above 10°C (50°F).
- The relative humidity must be below 80%. Good airflow with the use of large fans may be necessary to assist in the water release.
- Very high humidity with poor air circulation would greatly slow water release and drying. This may lead to water entrapment, mud cracking, and poor adhesion.
- Do not apply a thick film of the primer as water may become trapped.
- It is always recommended to apply **ZeraDite™ W** in a thin film to avoid roller marks.
- Do not apply to steel or polyurethane sealants.

COVERAGE

6.7 m²/litre (275 ft²/U.S. gallon)

PACKAGING

3.79 liter (1 U.S. gal.) units for both

CLEAN UP

Clean all equipment and installation tools immediately with water.

STORAGE

Store in a heated warehouse. Do not freeze.

SHELF LIFE

One year from the date of manufacture if kept in the original unopened containers under normal heated warehouse conditions.

SAFETY PRECAUTIONS

Consult Material Safety Data Sheet (MSDS) for specific instructions.

WARRANTY

“The recommendations made and the information herein is the result of accurate laboratory and field tests under controlled conditions. We guarantee that the quality and properties of the materials supplied conform to our standards. Zeraus Products Inc. makes no warranties, expressed or implied, as uses and applications are beyond our control. Zeraus Products Inc. shall not be liable for any injury, loss, or damage (direct or consequential) arising from use or inability to use the products. Before using, the user is urged to pre-test the products in his/her own environment to determine the suitability of the products for their intended use, and the user assumes all risk and liability whatsoever in connection therewith.

Zeraus Products Inc.’s liability, if any, is limited to a refund of the purchased price or replacement of that portion of the merchandise proven to be defective. Zeraus Products Inc. shall have no other liability, including liability for incidental, consequential or resultant damages, however caused, whether due to breach of warranty, negligence, or strict liability.

This warranty may not be modified or extended by representatives of Zeraus Products Inc., its distributors or dealers.”