



# ZeraLite™ W Sealer

## Industrial Waterborne White Asphalt Sealer

### DESCRIPTION

ZeraLite™ W Sealer is based on a unique natural oil-based alkyd/acrylic hybrid latex technology. It produces a durable coating with good cure speed and film toughness. ZeraLite™ W Sealer has superior chemical resistance as compared to standard styrene acrylic emulsion chemistries. It protects against penetration by petroleum products , making cleaning easier.

### WHERE TO USE

ZeraLite™ W Sealer is designed primarily as a sealer for asphalt surfaces for commercial and industrial use such as commercial parking garages (white line paint), airplane runways and a variety of other demanding applications..

### BENEFITS

- Odourless & safe; non-toxic
- Very attractive semi gloss finish
- Easy to apply using a brush, roller or an airless spray
- Excellent adhesion to asphalt
- Outstanding colour stability and brightness
- Resistant to gasoline, oil, brake fluid and anti-freeze
- Excellent durability, UV and weathering resistance
- Best combination of dry time and flexibility

### Colours:

Offered only in white; other customs colours may be available based on a minimum orders and lead time.

### Handling Properties @ 23°C (74°F)

Viscosity (mixed), cps	thixotropic
Solids (weight)	64%
Solids (volume)	50%
Density (mixed)	1.18kg/litre (9.8 lb./US gal)
Re-coat time	4-5 hours
Full Cure and Maximum Resistance	5 day
<u>Chemical Resistance: 4 hrs spot test (1-10, 10+Best)</u>	
Oil	9
Brake Fluid	9
Gasoline	9
Anti-Freeze	10
Water	9

### SURFACE PREPARATION

ZeraLite™ W Sealer is recommended to apply 4 weeks after new asphalt installation. It should be applied over a clean, sound and dust free surface. For line paint application, Apply the tape carefully in a straight fashion

over the clean and prepared substrate. Gently rub over the tape to ensure that the tape is properly adhered to the surface with no voids beneath it.

### MIXING AND APPLICATION

The mixing equipment used to mix the coating must be clean and free of any contaminants that may be present in the equipment from previously used products. Mix ZeraLite™ W Sealer to eliminate the possibility of settlement.

Pour enough material onto paint tray and apply with a 9 mm lint free roller evenly in uniform fashion to provide an even film thickness of 8 mils we in a single application. Allow to dry for 5 hours and reapply. Remove the tape. Allow it to sufficiently cure prior to opening it to traffic. For sealer application over asphalt , apply the sealer just like paint. Mix and use.

### LIMITATIONS

- Minimum application and curing temperature is 12°C (54°F).
- Must be applied to properly clean surfaces
- Avoid puddling or applying the coating in a thick film as it may cause shrinkage, cracking, and poor adhesion
- This sealer would not prevent cracking, breaking up and in some cases delamination of a portion of the asphalt surfaces.

### COVERAGE

6 m²/L (250 ft²/U.S. gallon per coat)

### PACKAGING

18.9 litre (5 U.S. gal)

### CLEAN UP

Clean all equipment with potable water prior to dry.

### STORAGE

Protect from freezing. Store under normal heated warehouse conditions.

### WARRANTY

“The recommendations made and the information herein is the result of accurate laboratory and field tests under controlled conditions. We guarantee that the quality and properties of the materials supplied conform to our standards. Zeraus Products Inc. makes no warranties, expressed or implied, as uses and applications are beyond our control. Zeraus Products Inc. shall not be liable for any injury, loss, or damage (direct or consequential) arising from use or inability to use the products. Before using, the user is urged to pre-test the products in

his/her own environment to determine the suitability of the products for their intended use, and the user assumes all risk and liability whatsoever in connection therewith.

Zeraus Products Inc.'s liability, if any, is limited to a refund of the purchased price or replacement of that portion of the merchandise proven to be defective. Zeraus Products Inc. shall have no other liability, including liability for incidental, consequential or resultant damages, however caused, whether due to breach of warranty, negligence, or strict liability.

This warranty may not be modified or extended by representatives of Zeraus Products Inc., its distributors or dealers.”